














DESCRIPTION			
Total thickness	EN ISO 24346	mm	4.0
Backing	-	-	Jute fabric
Weight	EN ISO 23997	g/sqm	4700
Width of sheet	EN ISO 24341	cm	200
Length of sheet	EN ISO 24341	m	20 - 31
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 24011
European classification	EN ISO 10874	class	23 / 34 / 43
Fire rating	EN 13501-1	class	Cfl-s1*
Slip resistance	ASR A1.5 / DIN 51130 – BGR 181	class	R9
Barefoot slipping	DIN 51097	class	A
Impact sound insulation	EN ISO 717-2	dB	6 dB
PERFORMANCES			
Residual indentation	EN ISO 24343-1	mm	≤ 0.20
Colour fastness	EN ISO 105 - B02	degree	≥ 6
Point contact resistance	VDE 0100	kOhm	>200
Static electrical propensity	EN 1815	kV	app. 2.0
Castor chair test (Type W)	ISO 4918	-	OK
Thermal resistance	EN 12667	Sqm,K/W	0.023
Thermal conductivity	EN ISO 10456	W/(m.K)	0.17
Surface treatment	-	-	LPX
Chemical products resistance	EN ISO 26987	class	OK
Anti-bacterial activity (E. coli – S. aureus – MRSA)**	EN ISO 22196 (JIS Z 2801)	-	> 99,99% inhibits growth after 24h
CERTIFICATES AND LABELS			
      			
CE MARKING			
	EN 14041 : 2004 AC : 2006	-	   

\* Glued according to certificate.  
DOP numbers available from your local branch.

 Depending on light exposure, the product color can vary, due to linoleum natural oxidization process. The process is reversible.  
We recommend that the samples be exposed to sunlight for several hours prior to making a final color choice